



paint specification & estimated consumption

Owner : Hamburg-Sued
Size : 20' DV

Date : 18th December, 2008

<u>PRODUCT NAME</u>	<u>LOCATION</u>	<u>AREA(m²)</u>	<u>D.F.T.(u)</u>	<u>S.V.(%)</u>	<u>L.R.</u>	<u>S.R.(m²/L)</u>	<u>CON.(KG)</u>
Zinc rich epoxy primer M114-9173	S/P	156	10	49	0.50	24.50	15.28
Zinc rich epoxy primer M114-9173	External	65	20	49	0.50	12.25	12.73
Epoxy primer M131-7035	External	65	30	51	0.50	8.50	9.94
Acrylic topcoat M210-Ral 2002	External	65	60	42	0.40	4.20	18.57
		TOTAL:	<u>120</u>				
Zinc rich epoxy primer M114-9173	Internal	65	20	49	0.50	12.25	12.73
Epoxy topcoat M281-Ral 7035	Internal	65	60	58	0.50	4.83	17.48
		TOTAL:	<u>90</u>				
Zinc rich epoxy primer M114-9173	Base	22	20	49	0.50	12.25	4.31
		TOTAL:	<u>30</u>				
Thinner 9010030 (150% For shoppriming)							22.92
Thinner 9010015 (25% For M114,M131,M281)							14.30
Thinner 9030001 (20% For M210)							3.71
						TOTAL:	<u>131.99</u>