



## paint specification & estimated consumption

Owner : SCF  
 Size : 20' HC(20'x8'x9'6")

Date : 13th May, 2011

<u>PRODUCT NAME</u>	<u>LOCATION</u>	<u>AREA(m<sup>2</sup>)</u>	<u>D.F.T.(u)</u>	<u>S.V.(%)</u>	<u>L.R.</u>	<u>S.R.(m<sup>2</sup>/L)</u>	<u>CON.(KG)</u>	<u>price(RMB/KG)</u>	<u>amount(RMB)</u>
Zinc rich epoxy primer M114-9000	S/P	166	10	49	0.10	44.10	9.03	27.90	252.05
Zinc rich epoxy primer M114-9000	External	72	20	49	0.20	19.60	8.82	27.90	245.98
Epoxy primer M131-	External	72	40	51	0.50	6.38	14.68	17.00	249.60
Acrylic topcoat M210-	External	72	40	42	0.50	5.25	16.46	18.78	309.07
		<b>TOTAL:</b>	<b><u>110</u></b>						
Chemical resistance paint PE280-7035	Internal/floor	83	240	48	0.50	1.00	116.20	27.00	3137.40
		<b>TOTAL:</b>	<b><u>240</u></b>						
Zinc rich epoxy primer M114-9000	Base	11	20	49	0.20	19.60	1.35	27.90	37.58
		<b>TOTAL:</b>	<b><u>30</u></b>						
Thinner 9010030 (150% For shoppriming )							13.55	12.70	172.10
Thinner 9010015 (25% For M114, M131)							6.21	14.00	86.96
Thinner 9030001 (25% For M210)							4.11	14.00	57.60
Thinner T331 (10% For PE280)							11.62	14.60	169.65
							<b>TOTAL:</b>	<b><u>202.03</u></b>	<b>4717.98</b>
								in USD	<b>620.38</b>