

FAX NO.: 021-59168768

ATTN: Miss Judy Yin

FROM: Calvin Qiu



PAINT SPECIFICATION & ESTIMATED CONSUMPTION

OWNER: DECKWELL

SIZE: 20'

MANUFACTURER: SPIC

DATE: July 3,2002

CODE: DECKWELL20GP

<u>PRODUCT NAME</u>	<u>LOCATION</u>	<u>AREA(m²)</u>	<u>D.F.T.(u)</u>	<u>S.V.(%)</u>	<u>L.R.</u>	<u>S.R.(m²/L)</u>	<u>CON.(KG)</u>	<u>PRICE(\$/KG)</u>
Zinc epoxy shop primer M112	Shoppiming	152	10	51	0.15	43.35	6.14	1.68
Zinc rich epoxy primer M110	External	65	15	49	0.20	26.13	4.73	1.70
Zinc phosphate epoxy primer M130	External	65	40	48	0.30	8.40	10.06	1.52
C/R Topcoat M210	External	65	45	42	0.30	6.53	11.94	1.70
TOTAL:			110					
Zinc rich epoxy primer M110	Internal	65	10	49	0.20	39.20	3.15	1.70
Epoxy top coat M280-Ral7035	Internal	65	50	50	0.40	6.00	14.08	1.52
TOTAL:			70					
Zinc rich epoxy primer M110	Base	22	15	49	0.20	26.13	1.60	1.70
TOTAL:			25					
Thinner 9010030 (200% For M112)							12.27	0.92
Thinner 9010015 (25% For M110,M130,M280)							8.40	0.92
Thinner 9030001 (30% For M210)							3.58	0.92

TOTAL: 75.95

AMOUNT(\$)

10.31

8.03

15.29

20.30

5.36

21.41

2.72

11.29

7.73

3.30

105.73



Water based paint specification & estimated consumption

Owner : Hamburg-Sued
Size : 20' DV

Date : 18th November, 2011

PRODUCT NAME	LOCATION	AREA(m²)	D.F.T.(u)	S.V.(%)	L.R.	S.R.(m²/L)	CON.(KG)
Zinc rich epoxy primer M116-9174	S/P	156	10	49	0.10	44.10	8.49
Zinc rich epoxy primer M116-9174	External	65	20	49	0.30	17.15	9.10
Epoxy primer M150-7035	External	65	30	44	0.65	5.13	16.46
Acrylic topcoat M200-RAL 2002G	External	65	60	40	0.30	4.67	16.71
		TOTAL:	120				
Zinc rich epoxy primer M116-9174	Internal	65	20	49	0.30	17.15	9.10
Epoxy topcoat M170-RAL 7035	Internal	65	60	45	0.55	3.38	25.04
		TOTAL:	90				
Zinc rich epoxy primer M116-9174	Base	22	20	49	0.30	17.15	3.08
		TOTAL:	30				
Tap Water (50% For shoppriming)							
Cleaning Thinner T480 (For M116,M150,M170)							18.83
						TOTAL:	106.80