

DESCRIPTION

Mega WU 080 PU Pinhole Putty is a two-component and solvent free polyurethane putty for filling the pinholes in the substrate.

RECOMMENDED USE

As a pinhole putty for filling the pinholes in the FRP surface.

PHYSICAL CONSTANTS

Curing agent:	Mega WU 080B
Catalyzator:	Mega WU 150C, 0-2% by weight
Finish:	Gloss
Colours:	Bule
Weight solids:	Approx. 100%
Dry to touch:	<3h (20°C)
Fully cured:	7days (20°C, R. H. : 50%)
Shelf time:	12 months (20°C)

APPLICATIONS DETAILS

Curing agent:	Mega WU 080B
Mixing ratio:	Mega WU 080A:Mega WU 080B=3:2 (by weight)
Application method:	Knife
Thinner:	T764 (Forbidden when the defect was deeper than 2mm.)
Pot life:	10min (20°C, without catalyzator)
Cleaning of tools:	Thinner
Recoat interval:	See remarks
Surface preparation:	Cleaning oil and grease firstly, and then grinding the substrate.
Application conditions:	R.H. <85%, substrate temperature is higher than of dew point at least 3 degree.
Subsequent coat:	Grinding is required before any recoating.

REMARKS

- 1) Putty is sensitive to humidity. Re-sealing the rest of putty in time.
- 2) Drying time is based on the amount of catalyzator.

NOTE

This production is for professional use only.

Mega WU 080

PU PINHOLE PUTTY

SAFETY

Packings are provided with applicable safety labels which should be observed. In addition, national or local regulations should be followed. As a general rule, inhalation of solvent vapours or paint mist, and contact of liquid paint with skin and eyes, should be avoided. Forced ventilation should be provided when applying paint in confined spaces or stagnant air. Even when ventilation is provided, respiratory, skin and eye protection are always recommended when spraying paint.

OTHER NOTICE

All information in this product data sheet is based on standard conditions and slight variation may occur with different conditions. All information in our company is subject to change without notice.